




CIDB PPS REG. NO: 1160504ML0121



Premium Series

SN3-FR+



Excellent Reflectivity
(99% on both surface)



Chicken Wire Mesh
(Not Required)
Extra Heavy Duty
Tensile Strength



Edge Tear Resistance
(Extra Heavy Duty)



Moist Barrier
Non-Delamination
(When Soak In Water)



Easy Installation
(Cost Effective)



Noise Reduction

Product Description

SUN-FOIL® SN3-FR+ is used as insulation against radiant heat transfer and can be used to its greatest advantage in instances where radiation is the predominant means of heat transfer.

SUN-FOIL® SN3-FR+ is an excellent reflector of all long wave radiant heat that strikes it - **DOUBLE SIDED REFLECTIVE OF UP TO 99%** of all radiant heat.

Fire Attributes

SN3-FR+ is classified as Class "O" in accordance to fire tests on building material and structures.


- i.) British Standard, BS 476-6 : Fire Propagation Test
- ii.) British Standard, BS 476-7 : Surface Spread of Flame Test

Thermal Properties

R-value, thermal resistance varies depending on the roof design and total roof configuration. Please contact our specialist for roof system that complying UBBL and Malaysia Standards.

Awards & Certificates

- Malaysia Standard - MS 2095, SIRIM QAS International Sdn. Bhd.
- ISO 9001: 2015 & ISO 14001: 2015
- Jabatan Bomba dan Penyelamat Malaysia
- CIDB Malaysia
- Malaysia Green Building Confederation (MGBC)
- Asian Reflective Foil Association (ARFA)



IMPRESSIVE APPEARANCE



MAXIMIZE STRENGTH



ISO 9001:2015, ISO 14001:2015
CERTIFICATE NUMBER: JQS-23-0557, JES-23-0284

MyHP00220/22

SUN-FOIL® SN3-FR+ is made by double sided high reflectivity pure aluminium bonded with a layer of 6mm bubble diameter FR polyethylene bubble sheet reinforced with a layer of FR HDPE woven fabric. It provides excellent insulation properties and effective radiant barrier.

SUN-FOIL® SN3-FR+ is designed light-weight. It is easy to install as it does not require mesh due to extra high tensile strength and edge tear resistance.

SUN-FOIL® SN3-FR+ is also flame retardant, waterproof, non-toxic, bacteria free, fungus and corrosion resistant.

TECHNICAL DATA

Description	Test Method	Unit	Value
Grammage	In House	g/m ²	250 ± 50
Thickness	In House	mm	2.5 ± 0.5
Tensile Strength	AS/NS 1301:448s	kN/m	MD ≥ 10.0 ± 2.0 CD ≥ 10.0 ± 2.0
Edge Tear	TAPPI T470	N	MD ≥ 250 ± 50 CD ≥ 250 ± 50

Technical Information provided represent average result of tests conducted under standard procedure and is subject to variation. No guarantee can be made regarding specific applications or patent rights.

BQ SPECIFICATION


One layer of approved YH “SUNFOIL” SN3-FR+ Plus (250g/m²) Double Sided Fire Retardant Pure Aluminium Bubble Foil with 2mm thickness and 6mm bubble diameter reinforced with a layer of 10 x 10 inch woven fabric approved with Sirim Eco Label (35-40% energy reduction) and MS 2095.

FIRE RETARDANT TEST FOR SN3-FR+

CHARACTERISTIC	TEST METHOD	SPECIFICATION
Fire Propagation of Material Sub-Index, i_1, i_2, i_3 Overall Performance Index	BS 476 ; Part 6	< 6 < 12 (Sirim Report 2019FE0149)
Surface Flame Spread Test	BS 476 ; Part 7	Class 1 (Sirim Report 2019FE0150)
Classification of Fire Hazard		Class O



SN3-FR+ Standard Roll Size: W 1.20m x L 50m



YH LAMINATED PRODUCTS SDN. BHD. (959828-V)

Main Office : Lot 2996, Jalan PK 6, Kawasan Perindustrian Krubong, 75250 Melaka.
Sales Office : Lot 8352, Jalan PK SE, Kawasan Perindustrian Krubong, 75250 Melaka.
Factories : Lot 2995, Lot 8342, Lot 8343, Lot 8349, Lot 8350, Lot 8408, Kawasan Perindustrian Krubong, 75250 Melaka.



Sales Office Tel : +606-337 2170
Fax (Sales) : +606-335 7170
Fax (Finance) : +606-335 7199

Distributed by:

